

## Test results VentureClad Plus 1579

IMO 61 (67):Annex 1 Part 5 - Surface Flammability

IMO 61 (67):Annex 1 Part 2 - Smoke and Toxicity

Warrington Fire Research Report 10 Dec. 2003

		Tested	Limiting Values	
			Bulkheads	Flooring
<b>Approval for surface flammability</b>				
Critical flux at extinguishment (CFE)	kW/m <sup>2</sup>	> <b>50,5</b>	> 20	> 7,0
Heat for sustained burning (Qsb)	MJ/m <sup>2</sup>	> <b>30,3</b>	> 1,5	> 0,25
Total heat release (Qt)	MJ	< <b>0,01</b>	< 0,7	< 2,0
Peak heat release (Qp)	kW	< <b>0,01</b>	< 4,0	< 10,0

		Tested	Limiting values
Total heat release (Qt)	MJ	< <b>0,01</b>	< 0,2
Peak heat release (Qp)	kW	< <b>0,01</b>	< 1,0